




## AMF TOPIQ® Prime Hygena



- AMF TOPIQ® Prime Hygena is a very light stone wool panel with a modern, smooth surface. The surface is washable and anti-microbial (resistant to the growth of germs, bacteria and fungi)
- Excellent sound absorption (0.95  $\alpha_w$ )
- Excellent light reflectance (88%)
- ISO 5
- Ideal for healthcare facilities in general, kitchens, food industries, laboratories, etc.



<b>Edge details</b>  Additional edge details on request		Board 	Tegular 24/90 	Tegular 15/90 														
<b>Thickness (mm)</b>		15	15	15														
<b>Dimensions (mm)</b>  Additional sizes on request		610 x 610 625 x 625 1220 x 610 1250 x 625	610 x 610 625 x 625	610 x 610 625 x 625														
<b>System</b>		Exposed demountable - System C																
<b>Weight</b>		2.1 kg/m²																
<b>Colour</b>		White																
<b>Sound absorption</b>		EN ISO 354 $\alpha_w$ = <b>0.95</b> as per EN ISO 11654 - <b>Class A</b> <table><tr><td>Frequency <i>f</i> (Hz)</td><td>125</td><td>250</td><td>500</td><td>1000</td><td>2000</td><td>4000</td></tr><tr><td><math>\alpha_p</math></td><td>0.50</td><td>0.85</td><td>0.95</td><td>0.90</td><td>1.00</td><td>1.00</td></tr></table> NRC = <b>0.90</b> as per ASTM C 423			Frequency <i>f</i> (Hz)	125	250	500	1000	2000	4000	$\alpha_p$	0.50	0.85	0.95	0.90	1.00	1.00
Frequency <i>f</i> (Hz)	125	250	500	1000	2000	4000												
$\alpha_p$	0.50	0.85	0.95	0.90	1.00	1.00												
<b>Sound attenuation</b>		EN ISO 10848-2 $D_{n,f,w}$ = <b>24 dB</b> as per EN ISO 717-1  CAC = <b>24 dB</b> as per ASTM E 413-10																
<b>Sound reduction</b>		EN ISO 10140-2 $R_w$ = <b>13 dB</b> as per EN ISO 717-1																
<b>Fire reaction</b>		Euroclass <b>A1</b> as per EN 13501-1 <b>Class A</b> as per ASTM E 84  RUS <b>KM2 (G1, V2, D1, T1)</b> as per 123-FZ																
<b>Light reflectance</b>		<b>88%</b>																
<b>Humidity resistance</b>		<b>100% RH</b>																
<b>Clean room</b>		<b>ISO 5</b> as per EN ISO 14644-1																
<b>Indoor air quality</b>		 A	 E1															
<b>Cleanability</b>																		
<b>Sustainability</b>	 EN ISO 14021 33%	 BIOSOLUBLE WOOL EC 1272/2008 Annex Q																

Products may vary from country to country. Please contact your local sales representative.  
For further information and legal notice, please visit our website.